

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
30 September 2004 (30.09.2004)

PCT

(10) International Publication Number
WO 2004/083144 A1

- (51) International Patent Classification⁷: **C03C 1/00**
- (21) International Application Number:
PCT/EP2004/002577
- (22) International Filing Date: 12 March 2004 (12.03.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
NO2003A000005 21 March 2003 (21.03.2003) IT
- (71) Applicant (for all designated States except US): **NOVARA TECHNOLOGY S.R.L.** [IT/IT]; Via Fauser, 4, I-28100 Novara (IT).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **COSTA, Fulvio** [IT/IT]; Via Roma, 92, I-27048 Sommo (IT). **COSTA, Lorenzo** [IT/IT]; Via Roma, 92, I-27048 Sommo (IT). **SPARPAGLIONE, Massimo** [IT/IT]; Via Gorizia, 1, I-20097 S. Donato Milanese (IT).
- (74) Agents: **WEBER, Wolfgang** et al.; c/o Degussa AG, Intellectual Property Management, Postfach 13 45, 63403 Hanau (DE).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR).
- Declaration under Rule 4.17:**
— of inventorship (Rule 4.17(iv)) for US only
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2004/083144 A1

(54) Title: HIGH HOMOGENEITY SILICA GLASS PREPARED THROUGH A SOL-GEL PROCEDURE


(57) Abstract: The present invention relates to a Si₂O glass characterized by a high homogeneity, prepared through a sol-gel procedure.

HIGH HOMOGENEITY SILICA GLASS PREPARED THROUGH A SOL-GEL PROCEDURE

The present invention relates to a highly homogeneous Si₂O
5 glass prepared through a sol-gel procedure.


The sol-gel term defines a wide variety of processes which,
even if being different as for as the working details or
the reagents are concerned, are characterized by the
following common operations:

- 10 - preparation of a solution, or a suspension, of a
precursor formed by a compound of the element (M) the
oxide of which has to constitute the final glassy
article;
- hydrolysis, acid or base catalyzed, of the precursor,
15 inside the solution or suspension, to form M-OH groups
according to the reaction



wherein X generally is an alcohol residue and n means
the element M valence; the alcoxydes M(OR)_n can be
20 replaced by soluble salts of the element M such as
chlorides or nitrates, and, in some cases, oxides. The
obtained mixture, i.e. a solution or a colloidal
suspension, is named sol;

- polycondensation of the M-OH groups according to the
25 reaction



which requires a time from few seconds to some days,
depending on the solution composition and the
temperature; during this step, a matrix is formed

called, case by case, alcohogel, hydrogel or more generally, gel;

5 - gel drying till the formation of a porous monolithic body; during this step, the solvent is removed through a simple controlled evaporation, which determines the so called xerogel, or through an extraction in autoclave which determines the so called aerogel; the obtained body is a porous glass, which may have an apparent density of 10% to about 50% of the theoric density of the oxide having the same composition; the dried gel can be industrially used as such;

10 - densification of the dried gel by a treatment at a temperature, generally ranging between 800°C and 1500°C, depending on the gel chemical composition and the preceding step process parameters; during this step the porous gel is becoming dense, under a controlled atmosphere, till to obtain a glassy or ceramic compact oxide having the theoric density, with a linear shrinkage equal to about 50%.

20 The final densification let a glassy product be obtained having good general characteristics, and, however, without any such optical homogeneity property to let the material be crossed by the transmitted light wave front without any suffered distortion.

25 The Applicant has found that in the case suitable treatments under controlled atmosphere are carried out during the densification stage, the final glassy product is obtained having no streak and strip, the same being consequently characterized by an almost total homogeneity.

Therefore, the object of the present invention is a silica glass characterized, inter alia, by the following specific properties:

- 5 - light internal transmittance in the wave length between 185nm and 193nm higher than 85%
- light internal transmittance in the wave length between 193nm and 2600nm higher than 99.5%
- light internal transmittance in the wave length between 2600nm and 2730nm higher than 99%
- 10 - light internal transmittance in the wave length between 2730nm and 3200nm higher than 85%
- no streak, material of class 4 or better according to the rule DIN ISO 10110-4
- no strip
- 15 - no signal in the shadography (no shadow or intensity change)

such a silica glass being prepared according to a sol-gel process wherein, in the meanwhile the densification is achieved, a treatment is carried out by means of an
20 atmosphere containing water traces.

Claims

1. Silica glass characterized by the following specific properties:

- 5 - light internal transmittance in the wave length
 between 185nm and 193nm higher than 85%
- light internal transmittance in the wave length
 between 193nm and 2600nm higher than 99.5%
- 10 - light internal transmittance in the wave length
 between 2600nm and 2730nm higher than 99%
- light internal transmittance in the wave length
 between 2730nm and 3200nm higher than 85%
- no streak, material of class 4 or better according to
 the rule DIN ISO 10110-4
- 15 - no strip
- no signal in the shadography (no shadow or intensity
 change)

20 such a silica glass being prepared according to a sol-
 gel process wherein, in the meanwhile the densification
 is achieved, a treatment is carried out by means of an
 atmosphere containing water traces.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/002577

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C03C1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 063 179 A (MENASHI JAMEEL ET AL) 5 November 1991 (1991-11-05) the whole document	1
X	TSENG T Y ET AL: "Various atmosphere effects on sintering of compacts of SiO/sub 2/ microspheres" J. MATER. SCI. (UK), JOURNAL OF MATERIALS SCIENCE, OCT. 1986, UK, vol. 21, no. 10, 1986, pages 3615-3624, XP001189680 ISSN: 0022-2461 the whole document	1
X	US 5 068 208 A (HAUN NIELS ET AL) 26 November 1991 (1991-11-26) column 6, line 6 - line 14	1
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

23 June 2004

Date of mailing of the international search report

05/07/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Somann, K

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP2004/002577

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 310 486 A (SHINETSU CHEMICAL CO) 5 April 1989 (1989-04-05) column 8, line 37 - column 9, line 4	1
X	US 4 681 615 A (KANBE SADA O ET AL) 21 July 1987 (1987-07-21) examples	1
X	US 6 360 564 B1 (UKRAINCZYK LJERKA ET AL) 26 March 2002 (2002-03-26) column 7, line 45 - line 50	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/002577

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5063179	A	05-11-1991	AT 115519 T AU 7481291 A DE 69105955 D1 DE 69105955 T2 EP 0517841 A1 JP 5505167 T JP 3274466 B2 WO 9113040 A1	15-12-1994 18-09-1991 26-01-1995 20-04-1995 16-12-1992 05-08-1993 15-04-2002 05-09-1991
US 5068208	A	26-11-1991	NONE	
EP 0310486	A	05-04-1989	JP 1087522 A JP 7035256 B JP 1087523 A JP 2004371 C JP 7035257 B DE 3869308 D1 EP 0310486 A2 US 4883521 A	31-03-1989 19-04-1995 31-03-1989 20-12-1995 19-04-1995 23-04-1992 05-04-1989 28-11-1989
US 4681615	A	21-07-1987	JP 1024735 B JP 1542618 C JP 60065732 A JP 60065733 A JP 1573634 C JP 59116135 A JP 64000331 B JP 1833144 C JP 60131833 A DE 3390375 C2 DE 3390375 T EP 0131057 A1 GB 2140408 A ,B HK 69589 A WO 8402519 A1 NL 8320410 A ,C NL 8320410 T SG 39588 G US 4801318 A	12-05-1989 15-02-1990 15-04-1985 15-04-1985 20-08-1990 04-07-1984 06-01-1989 29-03-1994 13-07-1985 30-11-1989 07-02-1985 16-01-1985 28-11-1984 08-09-1989 05-07-1984 01-11-1984 01-11-1984 27-01-1989 31-01-1989
US 6360564	B1	26-03-2002	AU 1919101 A CA 2396955 A1 CN 1423623 T EP 1254078 A1 JP 2003520180 T WO 0153223 A1	31-07-2001 26-07-2001 11-06-2003 06-11-2002 02-07-2003 26-07-2001